

* For Premium and Textured colors, we recommend that all materials must be ordered together as paint color may vary color to color. † Weathering and appearance variation, including color, sheen, and spangle, is common in

T weathering and appearance variation, including color, sheen, and spangle, is common in non-painted materials and is not a cause for rejection. For consistent appearance, choose a paintfinished product.

Colors on this chart are close representations of actual metal color, limited by printing and viewing conditions. Color matching optimized for outdoor viewing. Customers should view an actual material sample before making a final color selection.

Contact your sales representative for accurate pricing.

SHERWIN-WILLIAMS. Coil Coatings

Choose an energy efficient paint finish.


Solar Reflectivity is the metal panel's ability to reflect sunlight. This characteristic of metal roofing is the most important in terms of energy savings. Cool metal roofing reflects much of the sun's rays, making the surface of the metal much cooler than material with a lower solar reflectivity rating.

Emissivity is the metal panel's ability to release absorbed heat. A low emissivity rating means the material will be hot to the touch (it doesn't release the heat), while material with a higher emissivity rating will be cooler to the touch. Therefore, metal with a low emissivity rating retains heat and may be more desirable for a cooler climate, while a high emissivity rating reflects heat and is more effective for saving energy in a warmer climate.

COLOR	INITIAL SOLAR REFLECTIVITY	INITIAL EMISSIVITY	SRI VALUE
Ash	0.32	0.84	32
Autumn	0.26	0.84	24
Brite	0.65	0.85	78
Bronze	0.27	0.86	26
Dark Bronze	0.27	0.85	26
Evergreen	0.26	0.84	24
Galvalume [®] (Acrylic Coated)	0.69	0.19	62
Sand	0.48	0.86	54
Slate Gray	0.18	0.88	15
Smoke	0.32	0.85	32
Terratone	0.32	0.87	33
Tudor	0.26	0.86	32
Matte Black	0.26	0.85	24

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Panels are unwashed. The Sherwin-Williams company certifies these tests to be true and accurate and performed by their laboratory.

For information on energy savings, visit centralstatesco.com/sustainability



Central Seam Plus[®] - 3" Mechanically Seamed Structural Recommended minimum pitch - 1/4:12 | Purlin spacing - 5'



Central SpanTM - 2" Mechanically Seamed Structural Recommended minimum pitch - 1/4:12 | Purlin spacing - 5'



Central Snap[®] - 1 ¾" Snap-lock Recommended min. pitch - 1:12 | Non-structural panel perfect for light commercial applications.



Precision-Loc[™] - 1" Soffit and Wall Panel Concealed fastener panel with clean lines that complement a building's walls and soffits.





Copyright © 2025, Central States Manufacturing, Inc., All Rights Reserved. CentralGuard" is a trademark of Central States" Manufacturing, Inc. Galvalume" is a registered trademark of BIEC International, Inc Fluropon" is a registered trademark of the Sherwin Williams Company.