



CentralGuard[®] (Prime SMP, Ultra SMP, bare)

COLOR	INITIAL SOLAR REFLECTIVITY	3-YEAR SOLAR REFLECTIVITY	INITIAL EMISSIVITY	3-YEAR EMISSIVITY	INITIAL SOLAR REFLECTIVE INDEX (SRI)	3-YEAR SOLAR REFLECTIVE INDEX (SRI)
Alamo	0.64	0.62	0.86	0.87	77	74
Brilliant	0.69	0.67	0.86	0.86	84	81
Black	0.26	0.25	0.87	0.86	25	24
Brown	0.33	0.33	0.86	0.85	34	34
Burgundy	0.30	0.29	0.87	0.86	31	29
Burnished Slate	0.34	0.33	0.86	0.85	35	34
Charcoal	0.37	0.36	0.86	0.85	39	38
Colony	0.35	0.35	0.86	0.86	37	37
Copper Metallic (Fluropon)	0.39	0.39	0.86	0.86	42	42
Crimson	0.32	0.32	0.87	0.87	33	33
Desert	0.43	0.41	0.88	0.88	48	46
Fern	0.28	0.27	0.86	0.86	27	26
Forest	0.25	0.24	0.87	0.86	24	23
Gallery	0.27	0.26	0.87	0.87	27	25
Galvalume						
Galvanized						
Gray	0.46	0.45	0.86	0.85	52	50
Hawaiian	0.27	0.26	0.87	0.85	27	24
Hunter	0.35	0.34	0.86	0.85	37	35
Ivory	0.66	0.64	0.87	0.87	80	77
Light Stone	0.56	0.52	0.86	0.87	65	60
Ocean	0.30	0.29	0.87	0.88	31	30
Pewter Gray	0.46	0.45	0.88	0.87	52	51
Polar	0.65	0.63	0.87	0.88	81	78
Rustic	0.34	0.33	0.86	0.85	35	34
Tan	0.45	0.45	0.86	0.86	50	50
Taupe	0.38	0.39	0.86	0.85	41	42

Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Panels are unwashed. The Sherwin-Williams company certifies these tests to be true and accurate and performed by their laboratory.

